ATTENTION: HARDNESS BLOCKS FOR CALIBRATION ARE OPTIONAL

ATTENTION: NEED TO CONFIRM IF THE WORKPIECES ARE SUITABLE BEFORE PURCHASE

# **ULTRASONIC HARDNESS TESTER CODE ISHU-330**


- 1. For steel material
- 2. Test surface hardening layers (carburized, nitriding, high frequency hardened, etc.)
  3. Suitable for arc and conical surface
- 4. Suitable for small or light workpieces
- 5. Test large workpieces at any direction
- 6. Suitable for rough surfaces







test cylinder surfaces (use V-groove on the cover)



- Test force and time are not affected by the operator
- Quick testing, only 2 seconds
- Average and statistics test modes
- Memory of 1024 test results for browsing and output
- Automatic power off
- Anti-dust and waterproof

# cover









(included)

## **SPECIFICATION OF MAIN UNIT**

Hardness scale		HV, HB, HRC, MPa			
Range		100~940HV, 80~650HB, 20~70HRC, 370~1740MPa			
Resolution		1HV, 1HB, 0.1HRC, 1MPa			
Accuracy	НВ	±3%			
	HV	±3%			
	HRC	±1.5%			
Data output		USB			
Operating temperature		-20°C ~ +40°C			
Power supply		built-in rechargeable battery			
Dimension of main unit		120×60×25mm			
Weight of main unit		200g			

### STANDARD DELIVERY

1 pc
1 pc
2 pcs
1 pc
1 pc

	alloy steel					
	steel		S	stainless steel		
		ST	AST	SST		
	HRC					
	НВ					
	ΗV					
user scale —	U1					
	BACK				Œ	LECT)

select the material and scale, use the corresponding standard hardness blocks or workpieces for calibration (calibration of HRC, HB and HV for steel are already made, calibration is needed before use other materials and scales)

### **OPTIONAL ACCESSORY**

Probe B	ISHU-460-B	
Couplant	ISH-COUPLANT	
Hardness block HRC20~30	ISH-BHRC1	
Hardness block HRC45~50	ISH-BHRC2	
Hardness block HRC60~65	ISH-BHRC3	
Hardness block 150~250HV5	ISH-BHV5A	
Hardness block 400~500HV5	ISH-BHV5B	
Hardness block 650~750HV5	ISH-BHV5C	
Hardness block 75~125HBW10/1000	ISH-BHB10A	
Hardness block 175~250HBW10/3000	ISH-BHB10B	
Hardness block 400~500HBW10/3000	ISH-BHB10C	

## SPECIFICATION OF PROBE

of Edition of Trobe					
Туре	A (standard)	B (optional)			
Test force	50N	10N (small force)			
Application	general use	plating			
Maximum roughness of workpiece (Ra)	2.5µm	1.5µm			
Minimum weight of workpiece (direct measurement)	0.1kg <b>*</b>	0.1kg*			
Minimum thickness of workpiece (direct measurement)	1mm *	1mm *			
Minimum radius of workpiece	5mm	5mm			
Minimum thickness of surface hardening layer or plating	0.1mm	0.03mm			
Minimum test area	Ø1mm	Ø1mm			
Dimension and weight of probe	140ר37mm, 271g	145ר37mm, 271g			

 $<sup>^{</sup>f \star}$ If the weight or thickness of workpiece is less than required, the workpiece should be fixed or coupled on solid support.